

# Bio dolomer

*Biodegradable Polymers*

**Product Information**

*Version 1.6 August 2018*

## *Biodolomer® F50*

### **Product Description**

Biodolomer® F50 is a biodegradable biomaterial.  
Contains at least 50 % renewable resources.

It is basically a compound of a biodegradable aliphatic-aromatic copolyester (PBAT), polylactic acid (PLA) and calcium carbonate.

Biodolomer® F50 offers a great down gauging potential needed for very thin film applications like T-shirt bags, organic waste bags, and carry bags etc.

Biodolomer® F50 already contains plant based antiblocking and slip agents required for easy processing on film extrusion and film conversion equipment.

**GAIA BioMaterials AB**

📍 **Bunkagårdsgatan 13, 253 68 Helsingborg  
Sweden**

☎ **+46 (0)42 300 39 99**

✉ **info@gaiabiomaterials.com**

Biodolomer® F50 exhibits the following properties:

- Processing temperature between 150 - 170 Celsius
- Excellent process-ability on conventional blown film lines
- Down gauging to 10 µm possible, typical thicknesses: 15 -120 µm
- Good mechanical properties
- Good bag manufacturing process
- No odor
- Wet strength (e. g. Organic waste bag applications)
- Nice white translucent color
- Excellent welding properties
- Ready to use grade
- Decor printable by flexo printing. No corona treatment needed.
- Contains at least 50 % renewable resources

### **Certification of Compostability and Biodegradability**

Biodolomer® F50 fulfills the requirements of the existing standards for compostable and biodegradable polymers, because it can be degraded by microorganisms. The biodegradation process in soil depends on the specific environment (climate, soil quality, population of microorganisms).

### **Food Regulatory Status**

Biodolomer® F50 is one of the few compostable polymers, which complies in its composition with the European food stuff legislation for food contact, EU Directive 10 / 2011 / EC with amendment 2016/1416 and US food contact notification for the main components: e. g. FCN 178, 475 and 907. Specific limitations and more details are given on request. The converter or packer has to check the suitability of the article for the application.

### **Form Supplied and Storage**

Biodolomer® F50 is supplied as lenticular pellets in 1 t big bags. Temperatures during transportation and storage may not exceed 60 °C at any time. Storage time of unopened bags may not surpass 12 month at room temperature (23 °C).

### **Applications**

Biodolomer® F50 has been developed for the conversion to flexible films using a blown film process. In view of numerous factors influencing functionality and shelf life of Biodolomer® films and finished articles made thereof the production parameters have to be tested by the converters before utilization. Additionally sufficient field tests are required to ensure the right functionality of the articles made from Biodolomer® F50.

### Typical Basic Material Properties of Biodolomer® F50

\* see Quality Control

Property	Unit	Test Method	Biodolomer® F50
Mass Density	g/cm <sup>3</sup>	ISO 1183	1.28 ~ 1.45
Bulk Density	kg / m <sup>3</sup>	DIN EN ISO 60	800
MFI190 °C, 2.16 kg	g/10min.	ISO 1133	1 - 2
Melting Points	°C	DSC	110 - 120

### Typical Properties of Biodolomer® Blown Film, 18 µm

\*not to be construed as specifications



Property	Unit	Test Method	Biodolomer® F50
Tensile Modulus MD/TD	MPa	ISO 527	260 /130
Tensile Strength MD/TD	MPa	ISO 527	25 / 25
Ultimate Elongation MD/TD	%	ISO 527	480 / 570
Dart Drop	g	ASTM D 1709-04 Method A	220
Tear Resistance	mN	DIN EN ISO 6383-2	1686 / 420

#### Note

The information submitted in this document is based on our current knowledge and experience. In view of the many factors that may affect processing and application, these data do not relieve processors of the responsibility of carrying out their own tests and experiments; neither do they imply any legally binding assurance for a special purpose. It is the responsibility of those to whom we supply our products to ensure that any proprietary rights and existing laws and legislation are observed.

(August 2018)